

## Technical Data Sheet

# PLY2

**Description:** Sheets produced from high impact ABS with increased heat resistance (high heat)

### Mechanical properties:

			Test Method
Tensile yield strength 50 mm/min	MPa	43	ISO 527
Tensile elongation at yield 50 mm/min	%	2,7	ISO 527
Tensile modulus 1 mm/min	MPa	2140	ISO 527
Izod-notched impact strength 23 °C / -30 °C	kJ/m <sup>2</sup>	25 / 12	ISO 180/1A
Ball indentation hardness	MPa	90	ISO 2039

### Thermal properties:

			Test Method
Vicat softening temperature VST/B/50	°C	102	ISO 306
Heat deflection temp. 1.8 Mpa, annealed	°C	101	ISO 75-1

### Flammibility:

			Test Method
UL94 rating at 1.6 mm thickness	class	HB	UL 94
Horizontal burning speed, 2 mm thickness for uncoloured products	mm / min	55	ISO 3795

### Other properties:

			Test Method
Density at 23 °C	g/cm <sup>3</sup>	1,05	ISO 1183

Product in non halogenated.

**Note:** The above information is given in good faith, but no warranty, express or implied, is given.

Innograv GmbH, Leinenkamp 9, 27299 Langwedel-Darverden  
Tel. +49 (0) 42 32 / 94 58 – 0 Fax +49 (0) 42 32 / 94 58 – 58